

ViterClad M50 Cladding Coating

Product Description	A two pack recoatable polyurethane finish with a metallic finish, specially formulated for the maintenance and repainting of architectural cladding.					
Features & Use	<ul style="list-style-type: none"> Recommended for the maintenance of Corus Colorcoat HP200* and HPS200* cladding Expected system lifetime up to 15 years (depending on exposed environment and shade) Suitable for PVF2, Silicone Polyester & Polyester Cladding when applied over ViterClad Bonding Coat Suitable for urban, marine and industrial environments Tough, durable finish combining abrasion resistance with outstanding colour and sheen retention Good cleaning properties for ease of building maintenance Cures at sub-zero temperatures and has good climatic tolerance Tolerant of slight surface moisture during application 					
Approvals/ Certification	Recommended for the maintenance of Corus Colorcoat HP200* and HPS200* cladding					
Finish	Semi-gloss metallic					
Volume Solids	42 ± 2% (may vary with colour)					
VOC Content	471 ± 20 g/litre (varies with colour)					
Film Thickness Range And Coverage		Dry Film Thickness	Wet Film Thickness	Theoretical Coverage		
	Minimum	25 µm	60 µm	16.8 m ² /litre		
	Maximum	60 µm	143 µm	7.0 m ² /litre		
	Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated					
Drying Times	Applied to 50 microns DFT		+5°C	+10°C	+23°C	+35°C
	Dust Free		3 hr	2 hr	1 hr	45 min
	Hard Dry		9 hr	6 hr	3 hr	2 hr
	Overcoating	Minimum	24 hr	24 hr	12 hr	10 hr
		Maximum	Indefinite if clean and sound			
	Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation					
Colours	RAL9006, plus selected metallic range made to order					
Mix Ratio/ Product Code	Base	2900 919	8 parts by volume			
	Hardener	4054 122	1 part by volume			
Pot Life	4 hours at 23°C					
SG	1.06-1.08 kg/lit mixed, varies with colour					
Storage Conditions	Store in dry, cool conditions and protect from frost					
Shelf Life	Minimum 12 months if stored as above in unopened containers					
Flash Point	23-60°C					

ViterClad M50 Cladding Coating

<p>Surface Preparation</p>	<ul style="list-style-type: none"> • This product is a finish coat which should be applied over ViterClad Bonding Coat or suitably prepared, sound Plastisol for recolour work • For aged/degraded Plastisol, condition diagnosis and correct surface preparation are critical to performance. Please consult Axalta Coating Systems for individual project specifications • Completely new and unweathered HP200* Plastisol must be wiped with white spirit (1050 Thinner) and allowed to dry prior to applying ViterClad 50 • New HPS200* Plastisol must be wiped with xylene (1006 Thinner) and allowed to dry prior to applying ViterClad 50 • For PVF2, Silicone Polyester and other cladding types, refer to Axalta Coating Systems • Surfaces should be clean, dry and free from all grease, oil and general contamination
<p>Mixing</p>	<p>Mix only in the proportions stated, mixing each component individually then together using a mechanical agitator. Agitate periodically during use to ensure product remains homogeneous.</p>
<p>Thinner</p>	<p>1737 Thinner Equipment Cleaner 1737 Thinner</p>
<p>Application Conditions</p>	<p>Only apply in conditions of good ventilation which must be maintained during drying and curing. Do not apply in windy conditions where wind is likely to carry spray mist. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time of the paint coating, the surface should be dry, the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point. Only apply this product when the above conditions can be maintained throughout the critical application and drying/curing process. Paint temperature should ideally be at a minimum of 15°C. Do not apply above 40°C. Do not apply over standing or running water or ice.</p>
<p>Application Methods</p>	<ul style="list-style-type: none"> • Airless Spray: recommended for best finish. Output fluid pressure at tip 2000-2500 psi, Tip Size: 11-13 thou (0.33-0.43mm). Up to 5% 1737 Thinner may be added for application under cool or hot conditions, but thinning should be avoided if possible • Conventional spray is possible but not recommended • Brush – not recommended due to metallic finish • Roller – use only good quality short hair roller types of suitable width to accommodate the cladding profile and configuration – always work from a wet edge. Up to 10% thinner may be required – use <u>1048 Thinner</u> when applying by roller in warm conditions. Axalta Coating Systems strongly recommend that a feasibility test area is applied to confirm acceptable aesthetics are achievable
<p>Product Notes</p>	<ul style="list-style-type: none"> • Contains isocyanates – refer to Safety Data Sheet • This coating has not been tested to the standard of the new regulation 7(2) of the Building Regulations 2010, which came into force in Dec 2018 <i>* HP200 & HPS200 are registered Trade Marks of Corus UK Ltd.</i>
<p>Health & Safety</p>	<p>Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.</p>

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.