





**REPORT No.** 097718-2-a

CUSTOMER INDUSTRIA ESPAÑOLA PARA EL DESARROLLO E

INVESTIGACION, S.A. IEDISA

**CONTACT PERSON** LAURA GARCÍA

ADDRESS POL. IND. POLIVISO. C/ HERREROS 8

41520 VISO DEL ALCOR, SEVILLA (SPAIN)

PURPOSE REACTION TO FIRE CLASSIFICATION REPORT ACCORDING TO

EN 13501-1:2018

TESTED SAMPLE PAINT

REF.: "GSC EXTERIORES PREMIUM"

**RECEPTION DATE** 19.01.2022 and 29.03.2022

**TEST DATES** 09.02.2022 – 21.04.2022

**ISSUE DATE** 10.05.2022

TRANSLATION DATE 24.05.2022





Pablo Garmendia Technical Manager Fire Safety Laboratory

- The results set out in this report refer solely and exclusively to the material tested.

- This report shall not be reproduced, except in full, without the express authorisation of FUNDACIÓN TECNALIA R&I

(\*) Data provided by the customer. FUNDACIÓN TECNALIA R&I accepts no responsibility or liability for data provided by the customer.

- In case of a lawsuit, the original spanish version shall be taken as reference.

**TECNALIA RESEARCH & INNOVATION** 

Área anardi, 5 E-20730 Azpeitia (Gipuzkoa)

REPORT No.: 097718-2-a PAGE 1/3









## 1. PURPOSE OF THE REPORT

The purpose of this report is to determine the reaction to fire classification obtained by the white paint with reference "GSC EXTERIORES PREMIUM", as per standard EN 13501-1:2018: "Fire classification of construction products and building elements. Part 1: Classification using data from reaction to fire tests".

NOTE: This report does not imply any approval or certification of the product.

#### 2. DESCRIPTION OF THE SAMPLE SUBJECT TO **CLASSIFICATION**

The sample with reference "GSC EXTERIORES PREMIUM" is defined as a mineral paint. It is a white matte paint which TECNALIA staff applied over laminated gypsum, under the following application characteristics.

a) Density: 1.43 g/cm<sup>3</sup>

b) Performance: 5 m<sup>2</sup>/l for each coat

c) Substrate: 12 mm thick gypsum laminate of class A2-s1,d0.

d) Coats applied: Two coats were applied

e) Colour: White f) Appearance: Matte

g) Application method: Roller

The technical datasheet of said sample is included in the annex of the report 097718-1.

### 3. REPORT ON WHICH THE CLASSIFICATION IS BASED

ISSUING LABORATORY: **FUNDACIÓN TECNALIA R&I (Azpeitia location)** 

Bº Lasao, Área Anardi 5

20730 Azpeitia (Gipuzkoa), Spain

**TESTED SAMPLE:** MINERAL PAINT

COMMERCIAL REFERENCE: "GSC EXTERIORES PREMIUM"

TEST APPLICANT: INDUSTRIA ESPAÑOLA PARA EL DESARROLLO

E INVESTIGACION, S.A. IEDISA. POL. IND. POLIVISO, C/ HERREROS 8

41520 VISO DEL ALCOR, SEVILLA (SPAIN)

TEST REPORT No.: 097718-1-a

**ISSUE DATE:** 24.05.2022

TEST CONDUCTED: As per EN 13823:2020 and EN ISO 1716:2018

PAGE 2 / 3 REPORT No.: 097718-2-a









### **TEST RESULTS**

TEST METHOD	PARAMETER	RESULT
EN 13823:2020	FIGRA 0,2 MJ	0.0 W/s
	FIGRA <sub>0,4 MJ</sub>	0.0 W/s
	LFS < edge	YES
	THR 600S	0.52 MJ
	SMOGRA	0.00 m <sup>2</sup> /s <sup>2</sup>
	TSP 600S	16.01 m²
	Flaming droplets/particles	NO
EN ISO 1716:2018	HHV	1.96 MJ/kg

# 4. CLASSIFICATION

In accordance with standard EN 13501-1:2018, the white matte coating or paint, with reference "GSC EXTERIORES PREMIUM" received on 19 January and 29 March 2022, is given the following reaction to fire classification:

# Reaction to Fire Classification: A2-s1, d0

This classification is valid when the coating referenced as "GSC EXTERIORES PREMIUM" is used under the following conditions:

- a) As a construction product in all applications, with the exception of flooring.
- b) When the reference coating is applied to any end-use substrate made up of laminated gypsum boards, as well as to any end-use substrate of classes A1 and A2-s1,d0 (as per EN 13501-1).
- c) (\*\*) When the coating referenced as "GSC EXTERIORES PREMIUM" is applied with a performance of 5 m²/l or greater in each coat, with 2 paint coats maximum.

(\*\*) The activities marked with an asterisk are not covered by the ENAC accreditation.

REPORT No.: 097718-2-a PAGE 3 / 3

