

# Multi Surface Topcoat

## Information Sheet

Version 1 7 February 2023

HMG Multi Surface Topcoat is a twin pack polyurethane finish coat offering superior adhesion, durability and hardness for a variety of substrates. Easy to use over Brass, Copper, Stainless Steel, Zintec, Mild Steel, Aluminium, Anodized Aluminium, Glass Fibre, Glass, Perspex, Foamex, Plastic, Kevlar, and Galvanised Steel. It can also be used as an in-mould coating.

- Quick drying, touch dry in 15 – 20 minutes, recoat after 30 mins @ 20°C
- Easy application, 2 coats in a day, 8 hours pot life.
- Available in Gloss, Satin & Matt finish.  
Determined by base and hardener mix ratio, see application advise for details.
- Available in a wide colour range including BS, RAL, Industrial, Commercial Vehicle, HMG Colour Box.
- Coverage: 8 – 10m<sup>2</sup> per ltr at 50 microns WFT
- Thinner: HMG 2602

Manufactured under the auspices of an ISO 9001 management system.

## Information

<b>Theoretical Coverage (approx) at 20 microns DFT</b>	8-10m <sup>2</sup> per litre	<b>Number of Coats (Guide Only)</b>	Compliant 1 - 2 Coats Pressure Pot 1 - 2 Coats
<b>Drying time at 20°C (May vary with film build and temperature)</b>	Touch Dry - 15 - 20 mins Hard Dry - 2 - 3 Hours Full Dry - 7 Days	<b>Application</b>	Compliant or Pressure Pot
<b>Suggested Primer</b>	HS Epoxy/Zinc Rich Epoxy	<b>Spray Gun Setup</b>	Compliant 1.6 - 1.8 Pressure Pot 1.2 - 1.4
<b>Hardener</b>	9004	<b>Mixing Ratio</b>	Gloss - 5:1 Satin - 8:1 Matt - 9:1
<b>Thinner</b>	2602	<b>Wet Film (WFT)</b>	50 - 100 microns
<b>Thinning</b>	Compliant Spray up to 5% Pressure Pot up to 5%	<b>Dry Film (DFT)</b>	25 - 50 microns
<b>Flash Point</b>	26°C	<b>Pot Life</b>	8 hrs @20°C
<b>Volume Solids</b>		<b>Flash Off</b>	10 mins
<b>Maximum VOC (RFU)</b>	470g/l	<b>Finish</b>	Gloss, Satin, Matt
<b>Regulation / Compliance</b>		<b>Available Pack Sizes</b>	5L

## Important Information Before Use

Read and follow SDS, TDS, and label instructions. Stir paint thoroughly before use. Always use the same batch number on the same job. Check colour and sheen, HMG will not accept any discrepancies arising after use. Filter the product immediately before use. Reduce emissions and maintain quality by replacing tin lid after use. If in doubt, contact HMG Technical Service Department on 0161 205 7631.

## Substrates

HMG Multi Surface Topcoat is suitable as a primer coat for suitably prepared metals, clean and free of grease, oils and other contaminants. Not suitable for coating over bitumen or chlorinated rubber coatings.

## Application Climate

Substrate temperature should be 5°C or above for application and during cure, and a minimum of 3° above the dew point. Adequate dry air ventilation should be supplied during drying.

## Application Information

Thinning should only take place after material is thoroughly mixed. Application and use should always conform with the codes of practice described in BS 6150 and BS 5493.

## Surface Preparation

Ensure surfaces are clean, dry and free from grease, oils, dust and other contamination prior to application.

Thoroughly clean and degrease using suitable HMG Prep Clean 2802, 2803 or 2804.

Rust/corrosion to be removed to Sa or St standards, remove to clean metallic appearance with little or no rust/corrosion present. Areas where blast cleaning is not cost effective or practical, then the use of Ferrozinc is an alternative. Though Ferrozinc is not an equivalent alternative to shot blasting, it does offer a far superior performance than conventional coatings applied to slightly rusted surfaces. FERROZINC is used after simple wire brushing to remove surface rust, prior to application of primer.

## General Specification

### Bare steel substrates

**Mild Steel** – Remove millscale and thoroughly degrease using suitable HMG Prep Clean. Abrade with P80 – P180 if necessary, prior to application of primer.

**Shot Blasted Steel** – Remove all traces of blast grit/sand prior to application of primer.

**Aluminium** – Abrade with P180 – P320, degrease with suitable HMG Prep Clean prior to application of primer.

**Galvanised Steel** – Degrease with suitable HMG Prep Clean, apply HMG Mordant Wash, apply HMG Etch Primer and if required HMG Primer.

### Previously Painted

High pressure wash to remove all loose debris and poorly adhered previous coatings to remove all salts and other contaminants.

Degrease using suitable HMG Degreaser 2800 to remove grease and oils not removed with pressure washing alone. Existing coatings to be well adhered with all edges tight and well feathered. Rust/corrosion to be removed back to clean metallic appearance. In areas where complete removal or spot rust remains apply HMG Ferrozinc.

Abrade to provide good adhesion.

Wipe over with degreaser to remove loose debris from abrasion.

Substrate to be clean, free of grease, oils, dust and completely dry prior to application. For full surface preparation please refer to our web site for Knowledge Base article Prep Cleaning Techniques (KNB0009) and Preparatory Cleaners from the Product Guide. If in doubt speak to HMG Technical Department on 0161 205 7631.

## Health And Safety

Refer to SDS and tin label prior to use. Suitable respiratory equipment should be worn when spraying.

Contaminated rags, spray booth filters or other substrates should be segregated from other chemical waste, soaked with water or disposed of in a non-combustible container with tight fitting lid.

# Multi Surface Topcoat



Information Sheet

Version 1 7 February 2023

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is to the best of HMG's knowledge and belief accurate and reliable as of the date indicated. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy themselves as to the suitability and completeness of such information for their own particular use. For professional use only.