

## TECHNICAL DATASHEET

Issue date:  
March 2021

# SELEMIX® 2K POLYURETHANE DIRECT PRIMER

**GREY 4-0500                      BLACK 4-0502**  
**WHITE 4-0501                      RED 4-0503**

### PRODUCT DESCRIPTION

*Selemix 4-050x PUR Primer* is a high build 2K polyurethane primer which may be used in a wet on wet system. It gives good corrosion resistance and can be used on a range of different substrates. It uses the same Hardeners and thinners as *Selemix 2K Acrylic* and *Polyurethane* topcoats, giving a simple and compact system that is suitable for the finishing and protection of machinery, agricultural and construction equipment, and many other industrial painting applications.

### PRODUCTS

4-0500	<i>Selemix PU PRIMER GREY RAL 7035</i>
4-0501	<i>Selemix PU PRIMER WHITE</i>
4-0502	<i>Selemix PU PRIMER BLACK</i>
4-0503	<i>Selemix PU PRIMER RED</i>

#### Hardeners:

9-060	Extra PU Hardener
9-065	Slow Hardener
9-070	Direct Hardener
9-080	Acrylic Hardener

#### Thinners:

1-430	Acrylic Thinner
1-420	Polyurethane Thinner
1-208	Slow Thinner
1-470	Slow Direct Thinner

### SUBSTRATES AND PREPARATION







Steel (Blast Cleaned)	Blast clean to ISO 8501-1 SA 2.5 with a blast profile of maximum 40 µm Rz
Steel/Cast Iron	Machine sand with P80-120 discs and degrease
Galvanised steel	Abrade with Scotchbrite® and degrease
Light Alloys and Aluminium	Machine sand with P280-320 discs and degrease
Painted Surfaces	Machine sand with P240-320 discs and degrease
Fiber Reinforced Plastic	Machine sand with P240 discs and degrease






Apply only on a clean and dry surface with a temperature above the dew point to avoid condensation. In confined spaces, provide adequate ventilation during application and drying.

## MIXING


Thoroughly mix paint before activating and check colour before use

	Features Standard System	Conventional	Air-Assisted Airless
	<b>By Weight:</b> 4-050x Primer 9-060 / 9-065 Hardener Listed Thinner	1000 130 130 - 150	1000 130 100 - 150
	<b>By Volume:</b> 4-050x Primer 9-060 / 9-065 Hardener  Listed Thinner	5 1  0.65 – 0.75 (13 - 15%)	5 1  0.5 – 0.75 (10 – 15%)
	Features 9-080 Hardener	Conventional	Air-Assisted Airless
	<b>By Weight:</b> 4-050x Primer 9-080 Hardener Listed Thinner	1000 160 80 - 120	1000 160 0 - 80
	<b>By Volume:</b> 4-050x Primer 9-080 Hardener  Listed Thinner	4 1  0.5 – 0.8 (13 - 20%)	4 1  0 – 0.5 (0 – 13%)
	Features 9-070 Hardener	Conventional	Air-Assisted Airless
	<b>By Weight:</b> 4-050x Primer 9-070 Hardener Listed Thinner	1000 140 110 - 130	1000 140 100 - 130
	<b>By Volume:</b> 4-050x Primer 9-070 Hardener  Listed Thinner	5 1  0.65 – 0.75 (13 - 15%)	5 1  0.5 – 0.75 (10 – 15%)
	Features with any hardener	Conventional	Air-Assisted Airless
	Viscosity (at 20°C):  Pot Life (at 20°C):	20 - 35 secs DIN4  3 hours	35 - 45 secs DIN4  3 hours

## APPLICATION

	Features	Conventional	Air-Assisted Airless
	Spraygun setup:	Nozzle: Gravity: 1.6-1.8mm Suction: 1.8-2.0mm Pressure feed: 1.2-1.4mm	Tip: 11-13-15 thou (0.28-0.33-0.38 mm)
	Air Pressure:	Standard: 2.5-3 Bar	2.5-3 Bar
	Fluid Pressure:	N/A	70 -100 Bar
	Number of coats:	2	1 - 2
	Flash-off between coats:	10 - 15 min	5 - 10 min
	Drying:	bake at 60°C for 30-45 min	bake at 60°C for 30-45 min
	Flash-off before bake:	10-15 min	10-15 min
	Wet Film Thickness:	175-250 microns (90-150 microns per coat)	150-250 microns (75-125 microns per coat)
	Dry Film Thickness:	70-100 microns	70-120 microns

## DRYING TIMES

 at 20°C	Dust Free	20-30 min
	Touch Free	1 hour
	Handleable	2 – 3 hours
	Sandable after	4 – 6 hours
	Hard Dry	24 hours
	Stoving:	30-45 minutes @60°C (according to film thickness and hardener selection)
	Overcoating time:	Minimum: 2 hours (according to film thickness and hardener selection) Maximum: 72 hours without sanding on clean surface with any 2K <i>Selemix</i> Topcoat, or Selemix Basecoat
	Note:	Lower temperature or film thickness higher than 120µm will extend drying times

## TECHNICAL DATA

Based on ready-for-use mixed paint including thinner:	
VOC (g/L):	473-533 g/L (according to colour and dilution)
Solid content (weight):	58-66 %
Solid content (volume):	40-47 %
Solvent content (weight):	34-42 %
Specific gravity (Ready for use)	1.26-1.41 Kg/L
Theoretical coverage:	5.7-6.6 m <sup>2</sup> per litre at 70 microns DFT
Gloss:	Matt Finish

## PRODUCT CODES AND DESCRIPTIONS

Selemix Code	Short Code	Product Description	Packsize	
1.959.5060/E5	9-060	Extra PU Hardener	5	Lt
1.959.5065/E5	9-065	Hardener for Large Surfaces	5	Lt
1.959.5080/E5	9-080	Acrylic Hardener	5	Lt
1.991.5070/E5	9-070	Direct Hardener	5	Lt
1.991.3208/E5	1-208	Slow Thinner	5	Lt
1.911.4420/E5	1-420	PU Thinner	5	Lt
1.911.4430/E5	1-430	Acrylic Thinner	5	Lt
1.991.1470/E5	1-470	Slow Direct Thinner	5	Lt
2.705.0500/E20K	4-0500	PU Direct Primer Grey RAL7035	20	Kg
2.705.0501/E20K	4-0501	PU Direct Primer White	20	Kg
2.705.0502/E20K	4-0502	PU Direct Primer Black	20	Kg
2.705.0503/E20K	4-0503	PU Direct Primer Bright Red	20	Kg

## HEALTH AND SAFETY

For comprehensive Health, Safety and Environmental advice, please refer to the relevant Material Safety Data Sheets and Product can labels.

## THIS PRODUCT IS FOR PROFESSIONAL USE ONLY

The information given in this sheet is for guidance only. Any person using the product without first making further enquiries as to the stability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of our experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.

### FOR FURTHER INFORMATION PLEASE CONTACT:

Selemix Customer Service and Sales Group  
 Needham Road  
 Stowmarket, Suffolk  
 IP14 2AD, England  
 Tel: 01449 771771