

Technical Data Sheet

Rust-Oleum Universal All-Surface Brush Paint

A highly durable universal paint designed for direct application to many surfaces. Can be applied directly to wood, metal, most plastics, ceramics and even rust. No primer needed.

Preparation: Remove oil, grease and all other surface contamination by cleaning with appropriate detergents. Remove loose rust by scraping and wire brushing or sanding. Lightly abrade UPVC, remove any dust and wipe with methylated spirit.

Application: Stir thoroughly before use. Apply 1-2 coats with a brush or short pile mohair roller. For roller application lay off immediately with a brush. For best performance on non-ferrous or galvanised metals use Universal Special Metals Primer prior to application. For porous surfaces dilute first coat with 10% white spirit.

Coverage: Up to 9m²/litre. Coverage may vary depending upon method and rate of application and porosity of surface.

Drying Time: Touch dry in 2 hours. Handle after 8 hours. Apply a second coat after 16 hours if necessary. Full hardness is achieved after 7 days. Ensure application conditions are favourable for painting, we recommend that the temperature is between 10°C - 32°C with a maximum humidity of 80%, do not apply in direct sunlight or if conditions are humid.

Clean Up: Remove as much paint from brushes as possible before cleaning. Clean with a suitable brush cleaner or soak in white spirit for 5-10 minutes, rinse and dry thoroughly.

Limitations: Store in a dry, safe place. Do not store paint in environments where extreme temperatures may occur. Keep within 5-30°C. Do not store in direct sunlight. Whilst every effort is made to ensure the accuracy of colour, due to limitations of the print process, colour / finish shown is for guidance only.

Shelf Life: 2 years (unopened) from date of manufacture. (See base of can).

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. It is our recommendation that a trial area is first coated to ensure the product is satisfactory to individual requirements. A copy of the appropriate health and safety should be consulted prior to use.