



EP90 INSTRUCTIONS FOR USE

- Open Part A and stir gently for 1 minute or until homogenised
- Open Part B and pour the contents into the product in the Part A tin
- Stir mixture for 2 minutes or until well homogenised
- (Optional) Pour mixture into paint trays, separating mixture into parts according to the number of workers present
- Paint a single, thin coat onto the substrate, spreading out the material as much as possible without missing any areas
- Clean the equipment
- Allow unused material to cool for 2 hours before disposing of in normal waste to land fill site.

Notes:

- the application rate is 6-8 m² per litre
- the product will be sufficiently dry for overcoating in 4 hours
- the pot life is 45-60 minutes. Normally it takes 10 minutes to cover a square meter, so if using a 4L pack it may require two people painting simultaneously.