



Date (Oct 2021)

## PRETREATMENT OF HOT DIP GALVANIZED SURFACES

Zinc surfaces: Sweep blast-clean with mineral abrasives, e.g. quartz sand, to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with PANSARIPESU detergent.

Hot dip galvanized surfaces are recommended to be painted with a mist coat (paint thinned 25–40%) before the actual priming.

### Products suitable for hot dip galvanized surfaces:

Fontecryl 10	Temacoat SPA 50
Fontecryl 25	Temacoat SPA MIO
Fontecryl AP	Temacoat SPA Primer
Temaprime EE	Tematar TFA
Temaprime GF	Temadur 20
Temacoat Primer	Temadur Primer
Temacoat GF Primer	Temadur SC 50
Temacoat GPL-S Primer	Temadur SC 80
Temacoat GS 50	Temakeep
Temacoat HB 30	Temanyl MS Primer
Temacoat HB Primer	Temanyl PVB
Temacoat RM 40	

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.

TIKKURILA OYJ

P.O.Box 53, Heidehofintie 2, FI-01301 Vantaa, Finland, Tel. +358 20 191 2000

VAT FI01970674, Business Identity Code 0197067-4, Registered Office Vantaa

[www.tikkurilagroup.com](http://www.tikkurilagroup.com)